

SS100TD/ Ref 2(UK) Date 3.1.07 Issue No 9 1 of 3 Page No

SAFE STEP® 100 **Technical Data & Application Instructions**

Description

SAFE STEP® 100 is a single pack, epoxy ester anti-slip floor coating designed for application in areas of heavy pedestrian traffic. This high performance safety coating is easy to apply and offers optimum adhesion to metal, concrete and timber surfaces.

SAFE STEP® 100 has a shelf life of up to two years if stored in unopened containers. A partially used container may be resealed and saved for future use.

SAFE STEP® 100 resists petrol, oil, acids and aliphatic solvents. Refer to ROCOL Site Safety Systems for detailed performance data.

Technical Data (Typical)

Pack Size: 3.78 litres

Colour: Tile Red, Grey and Safety Yellow

Chemical Type: Single pack epoxy ester

Density: 1.67 Pot Life: Indefinite

Curing Times

light traffic: 12 hours @ 21°C 72 hours @ 21°C heavy traffic:

full chemical resistance: 7 days

Theoretical Coverage Per Pack

Spray: 5 m² Roller: 3.7 m² Trowel: 4.6 m² Shelf Life: 2 years Flash Point: 27°C Application Temperature: 10 - 40°C **Storage Conditions:** 10 - 30 °C

EU limited valve for this product (Cat A/i) This product contains max 385 g/l VOC.

:600g/I (2007) / 500g/I (2010)

Volume Solids: 61%

Coefficient of Friction ASTM F609

Drv: 1.17 1.00

Pendulum Slip Resistance (4S Slider - Product

applied by roller)

Dry - 94 (excellent) Parallel:

Wet - 86 (excellent) Oily - 75 (excellent)

Dry - 103 (excellent) Perpendicular: Wet - 99 (excellent)



Ref	SS100TD/
	2(UK)
Date	3.1.07
Issue No	9
Page No	2 of 3

Oily - 87 (excellent)

Surface Preparation

Apply SAFE STEP® 100 to clean, dry surfaces only. Remove all paint, rust and mill scale preferably by grit-blasting. Remove oil, dirt, wax, etc. by dissolving in a suitable water washable cleaner/degreaser.

All surfaces must be completely dry before application. Porous surfaces such as concrete and wood should be primed first using SAFE STEP® Non-Metal Primer to seal the surface. Metal surfaces should be primed with SAFE STEP® Metal Primer. New concrete should be allowed to cure for a minimum of 28 days before coating.

Application

- 1. SAFE STEP® 100 is a single component, epoxy ester coating.
- Thoroughly mix contents preferably with a mechanical mixer such as a pneumatic drill motor with a jiffy-mixing blade until mixed material assumes a uniform colour and appearance.
- 3. SAFE STEP[®] 100 can be applied at surface temperatures between 10°C and 40°C. Application is not recommended when surface temperature is above 40°C or below 10°C. At below 10°C curing time will increase substantially.
- 4. SAFE STEP® 100 can be applied by hard roller, trowel or spray equipment.

Application Techniques

For a tidy edge, mask off the area to be coated with masking tape. Remove masking tape whilst SAFE STEP® 100 is still wet by pulling away from the area.

Roller Application

Rolled application provides the most aggressive non-slip characteristics with an irregular, ridged surface.

 Only use a hard, phenolic coated, roller supplied by ROCOL Site Safety Systems for applying SAFE STEP[®] 100.

- 2. Pour a pool of the mixed product onto the prepared substrate.
- Roll material in one direction only, towards body in slow straight strokes using moderate pressure on the handle. Do not over-roll too many times or press down too heavily.
- 4. For maximum effect, rolling should be carried out perpendicular to the direction of traffic. Roll across ramps not down.

Trowel Application

Trowelled applications provide excellent antislip characteristics with a rough textured finish.

- Use a flexible bladed plasterer's finishing trowel approximately 10 x 30 cm. Wetting trowel with xylene will help improve surface finish.
- 2. Pour a pool of SAFE STEP® 100 onto the prepared surface.
- 3. Hold the trowel at 45 degrees angle to the surface. Pull material towards body with a sweeping motion reversing the angle on the opposite stroke.

Spray Application

Sprayed applications will result in a uniform appearance with good anti-slip characteristics and is an ideal method for large areas.

There are two types of spray equipment recommended for spraying SAFE STEP® 100. The choice depends on the size of the area to be coated.

Hopper Gun (for small areas up to 50m²)

Gun Type: Gravity fed hopper gun incorporating a 5mm nozzle, 5-litre hopper and elbow adapter for aiming at the floor. Air supply: 40-60psi air pressure. Ensure the air is oil free.



Ref SS100TD/ 2(UK) Date 3.1.07 Issue No 9 Page No 3 of 3

Spray the product in a linear motion at a distance of 40cm from the surface with an overlap of approximately 30%.

To clean equipment use xylene immediately after use.

Pressure Pot Sprayer (for large areas over 50m²)

Machine type: bottom outlet pressure pot nominally 30-50 litre capacity equipped with a double regulator and air driven agitator.

Air supply: typically 50cubic feet per

minute.

Fluid pressure: typically 2-3 bar (30-45 psi)

Fluid hose: 25mm diameter bore

reinforced pvc pipe

Atomising air pressure: typically 3-4 bar (45-

60 psi)

Tip diameter: 6mm

Fluid inlet to receive 25cm bore diameter pvc pipe. Air inlet to receive a 6mm-diameter airline.

With the spray nozzle removed and atomising air isolated slowly build up the fluid pressure to allow product to flow along the fluid pipe and through the gun into a container. This is done to prime the pipelines and remove any air. Note the pressure reading when the product is just flowing easily (i.e. jet of material reaching 40 - 50cm from gun). Switch off the air supply. Replace the spray nozzle and then rebuild the fluid pressure to the noted reading. Once product is flowing out of the nozzle begin to increase the atomising air pressure at the gun. As this pressure is built up the flow of product will form a spray pattern.

It is essential to match up the atomising air with the product fluid pressure, i.e. if the spray gun is not forming a spray pattern then there is not enough atomising air for the flow-rate. This can be remedied in one of two ways:

- 1. Reduce fluid pressure.
- 2. Increase atomising pressure.

Once an even spray pattern is achieved spraying can commence in a linear manner with approximately 30% overlap on each pass.

All components of the machine should be cleaned with xylene solvent immediately after use.

Surface Maintenance

It is essential that the SAFE STEP® 100 coating is cleaned regularly to maximise antislip performance. The use of a water based biodegradable detergent cleaner and a long handled fibre bristled brush or floor cleaning machine is recommended. After cleaning the surface should be rinsed thoroughly with clean water and allowed to dry.

Limitations

Higher temperatures will shorten drying time and conversely, lower temperatures and high relative humidity will lengthen drying time. Exterior applications must be protected from rain for at least 12 - 24 hours after application according to humidity. Protect from heavy rain or extended exposure to water, oil and chemicals for 5 to 7 days.

Health & Safety

Refer to Safety Data Sheet before use. If further copies are required or for further information, please contact us at the address below: