



Ref	SS500SF(UK) 5L kit
Date	21.3.06
Issue No	3
Page No	1 of 3

SAFE STEP® 500SF Technical Data & Application Instructions

Description

SAFE STEP® 500SF is a heavy duty, 100% solvent free two component epoxy anti-slip coating.

SAFE STEP® 500SF provides superior resistance to chemicals and wear. Its solvent free character allows its use in odour sensitive applications such as food processing facilities, hospitals etc.

SAFE STEP® 500SF is resistant to most common acids, alkalis, solvents, petrol, jet fuels and other hydraulic fluids.

Technical Data (Typical)

Pack Size:	5 litre
Colours:	Tile Red, Grey and Safety Yellow
Chemical Type:	Two pack solvent free epoxy
Mixed Density:	1.6
Pot Life:	30-40 minutes @ 20°C
Curing Times:	
Light Traffic:	24 hours @ 20°C
Heavy Traffic:	48 hours @ 20°C
Full Chemical Resistance:	7 days
Theoretical Coverage Per Pack:	
Roller:	2.7-4.7 m ²
Trowel:	5.4 m ²
Shelf Life:	2 years
Flash Point:	c.105°C
Application Temperatures:	10 - 30°C
Volume Solids:	100%
VOC Content:	0g/l
Storage Conditions:	10 - 30°C
TRL Slip Resistance - Pendulum method:	
Perpendicular:	Dry - 93 (excellent) Wet - 69 (excellent) Oily - 48 (excellent)

Surface Preparation

To ensure optimum adhesion of the floor coating it is vital that the correct quality and quantity of preparation is carried out initially.

Concrete should be at least 28 days old. Applying a coating onto concrete less than 28 days old could cause failure of the product.

All oils, grease, dirt, etc. must be removed using a suitable solvent or aqueous de-greaser solution.

ROCOL Site Safety Systems

ROCOL House, Swillington, Leeds, LS26 8BS, United Kingdom
Tel: +44 (0)113 232 2800 Fax: +44 (0)113 232 2850 Technical Helpline: +44 (0)113 232 2840
A Division of ITW Ltd. Registered Company No. 559693 VAT No. 742 0530 69

www.rocol.com

Registered Office: Admiral House, St. Leonards Road, Windsor, Berkshire, SL4 3BL



Ref	SS500SF(UK) 5L kit
Date	21.3.06
Issue No	3
Page No	2 of 3

All old coatings must be removed. This can be achieved by grit/shot blasting, scabbling or scarifying.

If the surface is not sufficiently rough to ensure a suitable key or where the surface of the concrete is weak the concrete must be etched using a suitable acid etch system if grit/shot blasting cannot be used.

Porous surfaces such as concrete and wood should be primed using SAFE STEP® Non-Metal Primer to seal the surface. Metal surfaces should be primed using SAFE STEP® Metal Primer.

For more detailed surface preparation on concrete or other surfaces contact the ROCOL Site Safety Systems Technical Department.

Application

SAFE STEP® 500SF is designed to be applied over a primer.

1. Pre-mix base component with a mechanical mixer such as a pneumatic drill motor with a jiffy mixing blade. Make sure all settlement is lifted off bottom of the container and is uniformly dispersed.
2. Pour entire contents of hardener can into base material and mix with a mechanical mixer (as above) for approximately 3-5 minutes or until mixed material assumes a uniform colour and appearance, scrape bottom and sides. Apply material immediately. No induction time is required.
3. Working pot (usable) life is approximately 30-40 minutes at 20°C. Pot life is increased at lower temperatures and decreased at higher temperatures.
4. SAFE STEP® 500 SF can be applied at surface temperatures between 10°C and 30 °C. Application is not recommended when surface temperature is above 30°C or below 10°C. At below 10°C curing time will increase substantially.

5. SAFE STEP® 500SF can be applied by hard roller or trowel.

Application Techniques

For a tidy edge, mask off the area to be coated with masking tape. Remove masking tape whilst SAFE STEP® 500SF is still wet by pulling away from the area.

Roller Application

Rolled applications provide the most aggressive non-slip characteristics with an irregular, ridged surface.

1. Use the SAFE STEP® 500SF Hard phenolic coated, roller for applying SAFE STEP® 500SF
2. Pour a pool of the mixed product onto the prepared substrate.
3. Roll material in one direction only, towards body in slow straight strokes using moderate pressure on the handle. Do not over-roll too many times or press down too heavily.
4. For maximum effect, rolling should be carried out perpendicular to the direction of traffic. Roll across ramps not down.

Trowel Application

Trowelled applications provide excellent anti-slip characteristics with a rough textured finish.

1. Use a flexible bladed plasterer's finishing trowel approximately 10 x 30 cm. Wetting trowel with xylene will help improve surface finish.
2. Pour a pool of SAFE STEP® 500 SF onto the prepared surface.
3. Hold the trowel at 45 degrees angle to the surface. Pull material towards body with a sweeping motion reversing the angle on the opposite stroke.

ROCOL Site Safety Systems

ROCOL House, Swillington, Leeds, LS26 8BS, United Kingdom
Tel: +44 (0)113 232 2800 Fax: +44 (0)113 232 2850 Technical Helpline: +44 (0)113 232 2840
A Division of ITW Ltd. Registered Company No. 559693 VAT No. 742 0530 69

www.rocol.com

Registered Office: Admiral House, St. Leonards Road, Windsor, Berkshire, SL4 3BL



Ref	SS500SF(UK) 5L kit
Date	21.3.06
Issue No	3
Page No	3 of 3

Surface Maintenance

It is essential that the SAFE STEP[®] 500 SF coating is cleaned regularly to maximise anti-slip performance. The use of a water based biodegradable detergent cleaner and a long handled fibre bristled brush or floor cleaning machine is recommended. After cleaning the surface should be rinsed thoroughly with clean water and allowed to dry.

Limitations

Higher temperatures will shorten curing times and conversely, lower temperatures and high relative humidity will lengthen curing times. Exterior applications must be protected from rain for at least 24 hours after application. Protect from heavy rain or extended exposure to water, oil and chemicals for 5 to 7 days.

Health & Safety

Refer to Safety Data Sheet before use. If further copies are required or for further information, please contact us at the address below:

ROCOL Site Safety Systems

ROCOL House, Swillington, Leeds, LS26 8BS, United Kingdom
Tel: +44 (0)113 232 2800 Fax: +44 (0)113 232 2850 Technical Helpline: +44 (0)113 232 2840
A Division of ITW Ltd. Registered Company No. 559693 VAT No. 742 0530 69

www.rocol.com

Registered Office: Admiral House, St. Leonards Road, Windsor, Berkshire, SL4 3BL